



**PRODUCT TECHNICAL DATA INFORMATION
EXTREME LIQUID STUCCO TEXTURE**

US COATING SOLUTIONS EXTREME LIQUID STUCCO is a specially formulated acrylic medium texture finish coating designed for application to above grade cementitious substrates, such as Stucco, Concrete Block, etc. Its special formulation allows for excellent alkali and efflorescence resistance, minimizes surface defects, provides excellent durability, resists fading and resists sagging, is mildew resistant, provides superior coverage and is easy to apply. **Mildew Resistant** - This paint contains agents which inhibit the growth of mildew on the surface of this paint film. **FOR INTERIOR & EXTERIOR USE!**

SUGGESTED PRODUCT USES: *SUITABLE FOR APPLICATION TO THE FOLLOWING PROPERLY PREPARED SURFACES:*

**CONCRETE * PLASTER * CEMENT COMPOSITION BOARD * MASONRY * CEMENT * BRICK * BLOCK * STUCCO
ALL CEMENTITIOUS & MASONRY TYPE SUBSTRATES**

SURFACE PREPARATION: The entire surface area to be painted should be clean, dry, sound and free from all dirt, dust, grease, oils, waxes, mildew, curing agents and any other surface contaminants. Remove any loose scale, chalked, cracked and peeling paint from previously painted surfaces by hand scraping, sanding, wire brushing and/or power tool cleaning. Repair all surface imperfections and cracks before application of coating. All cracks greater than 1/32" are to be routed open, dusted clean, sealed with **an, Alkali Resistant Masonry Primer** and allowed to dry properly. Pack the crack opening with a quality **Elastomeric Masonry Patching Compound** and allow to dry. Spot prime all repaired crack areas with above reference masonry primer. Cracks less than 1/32" should be detailed with **an Alkali Resistant Masonry Primer** and allowed to dry. Sand smooth all rough paint edges, as well as all rough surfaces. Prime all bare and/or new surface areas with Extreme Primer before application of this finish coating.

Mildew – Surface areas affected by mildew should be washed with US Coating Solutions Anti-Mold Soap. Rinse thoroughly with clean water, and allow a minimum of 24 hours to dry thoroughly.

PRODUCT SPECIFICATION DATA

- | | |
|--------------------------------|---|
| * COLORS: | White Only |
| * FINISH: | Flat |
| * FLASH POINT: | N/A |
| * METHOD USED: | T.C.C. |
| * COATING V.O.C.: | 0.55 LB/GAL. - (66 GRAMS/LTR.) |
| * SOLIDS: | By Volume: 44.40% ± 2% By Weight: 51.58% ± 2% |
| * RECOMMENDED MIL FILM: | Wet: 16.0 Mils - (Estimated At 100 Square Feet Per Gallon). Dry: 7.1 Mils - (Estimated At 100 Square Feet Per Gallon). |
| * ESTIMATED COVERAGE: | Covers approximately 80 - 100 square feet per gallon, depending on type of application and the porosity of the surface. |
| * CLEAN UP: | Water |
| * THINNING: | Clean Water |
| * ESTIMATED DRY TIME: | Dries to the touch in approximately 2 - 4 hours, for re-coat after 4 hours or overnight dry, depending on conditions. |

PRODUCT APPLICATION: **Alkali Resistant Acrylic Textured Masonry Finish** is specifically designed for spray application with a hopper type texture spray system, or an airless sprayer designed for texture spraying, such as the Graco TexSpray GM1030. Apply coating in such a manner as to yield a minimum 10 mil wet film build. It may also be troweled for various designs or troweled and back-rolled with a texture roller cover to achieve different texture styles. Always maintain a wet edge and avoid excessive respraying and reworking. Avoid painting outside weather conditions are threatening and late in the afternoon when there is a threat of moisture condensing on wet paint. Apply when surface and ambient temperatures are above 55_ F and below 90_ F. **KEEP FROM FREEZING!**

KEEP OUT OF REACH OF CHILDREN!

CAUTIONS: Avoid prolonged contact with skin, breathing of dust, vapors and/or spray mist. Avoid contact with eyes. **USE WITH ADEQUATE VENTILATION!** Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate properly-fitted respirator (NIOSH approved), during and after application. Follow respirator manufacturer's directions for respirator use. Use chemical safety glasses, goggles, or a face shield for proper eye protection. Wash thoroughly after handling and before eating or smoking.

KEEP FROM FREEZING! Close container after each use.

DO NOT TAKE INTERNALLY! Refer to Material Safety Data Sheet from your authorized US Coating Solutions representative for further safety and handling information.

FIRST AID: In case of skin contact, wash thoroughly with plenty of warm soap and water. In case of eye contact, immediately flush with plenty of water for 15 minutes, and get medical attention immediately. If you experience difficulty breathing, leave area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting, get medical attention immediately.

ALL OTHER WARRANTIES ARE EXCLUDED, WHETHER EXPRESSED OR IMPLIED BY OPERATION OF LAW OR OTHERWISE, INCLUDING ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SELLER SHALL NOT BE LIABLE, (DIRECTLY OR INDIRECTLY), UNDER ANY CIRCUMSTANCES FOR CONSEQUENTIAL, INCIDENTAL, SPECIAL OR ANY OTHER TYPE OF DAMAGES ARISING OR RESULTING FROM A BREACH OF WARRANTY UNDER THE SALE, HANDLING, OR USE OF THE GOODS SOLD OTHER THAN AS SET ABOVE. SELLER'S LIABILITY HEREUNDER, AND BUYER'S EXCLUSIVE REMEDY HEREUNDER, EITHER FOR BREACH OF WARRANTY, OR FOR NEGLIGENCE, ARE EXPRESSLY LIMITED TO THE REMEDY PROVIDED ABOVE. SELLER MUST BE GIVEN THE OPPORTUNITY TO INSPECT THE ALLEGEDLY DEFECTIVE MATERIAL. FAILURE TO GIVE THE REQUIRED NOTICE WITHIN THE TIME PROVIDED CONSTITUTES A WAIVER OF A CLAIM UNDER THIS WARRANTY.